

SEPIOLITA 4-30

HOJA DE ESPECIFICACIONES

Edición n°: 1

Análisis mineralógico (DRX)

Sepiolita.....	75%	Mín 65%
----------------	-----	---------

Densidad (BS 1460).....	0.61 g/cc	Máx 0.68 g/cc
-------------------------	-----------	---------------

pH (NF T 30-035).....	8.5	± 0.5
------------------------	-----	-------

Absorción Westinghouse

Agua.....	90%	Mín 80%
Aceite.....	40%	Mín 35%

Distribución granulométrica

> 6.00 mm	---
6.00-0.50 mm.....	Mín 98 %
< 0.50 mm.....	Máx 2 %

Fecha: Mayo 2.020

Pag: 1/1